


**DRY SIEVE ANALYSIS
TEST REPORT**



Project : Product Development
 Location : Foxton Plant
 Client : Mastermix and Packaging Ltd
 Contractor : na
 Sampled by : S Douglas
 Date sampled : 13/09/04
 Sampling method : Unknown
 Sample description : Joint-Loc, Joint Locking Sand
 Sample condition : As received, sealed, dry
 Bore hole no : na
 Depth (m) : na

Project No : 5WT033.M5
 Lab Ref No : 1393 (Report 1393.1A)
 Client Ref No :

Sieve Analysis							
Size (mm)	% Passing	Size (mm)	% Passing	Size (mm)	% Passing	Size (mm)	% Passing
75.00	-	19.00	-	4.75	-	0.425	43
63.00	-	13.20	-	2.36	100	0.300	28
37.50	-	9.50	-	1.18	91	0.150	12
26.50	-	6.70	-	0.600	61	0.075	6



Test Method	Notes
NZS 4407 : 1991 Test 3.8.2	History : As received Fraction tested : Whole Dispersant Used : Nil

Date tested : 29/09/04
 Date reported : 31/03/08

This report may only be reproduced in full

IANZ Approved Signatory

Designation : R Jones
 Date : 31/03/08



All tests reported herein have been performed in accordance with the laboratory's scope of accreditation